

# TITAN WOVEN COATED (RPE)

24mil WOVEN COATED GEOMEMBRANE



Commonly used for interim landfill covers and short-term liners. Titan 24mil Woven Coated Geomembrane is a medium-weight fabric incorporating a coating designed to improve toughness and abrasion resistance and is intended for exposed applications for up to 5 years.

## PRODUCT SPECIFICATIONS:

**Weave :** Woven black HDPE scrim  
**Coating :** LDPE 2.4mil average each side (57 g/m<sup>2</sup>/side)  
**Color :** Black, white or colored coatings available  
**Weight :** 9.1 oz/yd<sup>2</sup> (309 g/m<sup>2</sup>) ± 5%

## PERFORMANCE PROPERTIES:

The following data are typical values based on ASTM standard tests. This data should not be considered a specification.

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)	
			MD	TD
Thickness	ASTM D 1777	mil (mm)	Nominal 24 (0.60) ±10%	
Grab Tensile	ASTM D 7004	lbs (N)	370 (1645)	275 (1223)
Strip Tensile	ASTM D 7003	lb/in (N/5cm)	255 (2233)	190 (1664)
Tongue Tear - Large Scale	ASTM D 5884	lbs (N)	115 (512)	120 (534)
Mullen Burst	ASTM D 751	psi (kPa)	560 (3864)	
MVTR	ASTM E 96 Proc. BW	g/m <sup>2</sup> 24 hrs (perms)	0.23 (0.03)	
Hydraulic Conductivity (Permeability)	Calculated from MVTR	cm/s	9.79 x 10 <sup>-15</sup>	
Hydrostatic Resistance	ASTM D 751	psi (kPa)	262 (1805)	
Puncture Resistance	ASTM D 4833	lbs (N)	150 (666)	
CBR Static Puncture	ASTM D 6241	lbs (N)	993 (4409)	
Carbon Black Content	ASTM D 4218	%	3	
Dimensional Stability	ASTM D 1204	%	-2.9	-1.8
Low-Temperature Flex	ASTM D 2136-94	°C (°F)	Pass @ -65 (-85)	
HP-OIT	ASTM D 5885 (Measured on coating formulation)	Minutes	1071	
Accelerated UV Weathering	ASTM D 7238	after 10,000 light hours	> 90% strength retention	

## NOTES:

MD = Machine Direction. TD = Transverse Direction

i Q.U.V [A-340 Lamps]; 20 hrs UV @ 75°C; 4 hrs condensation @ 60°C

This data is provided for informational purposes only. Titan Environmental Containment Ltd. makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Titan Environmental Containment Ltd. for current updates.

**Titan Environmental Containment | Titan Environmental USA**

Toll free: 1-866-327-1957 | info@titanenviro.com | [TitanEnviro.com](https://TitanEnviro.com)

Rev. March 2025