## TE-M60 MONOFILAMENT GEOTEXTILE



Titan's Monofilament Geotextiles are manufactured using high-tenacity monofilament polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. These fabrics offer optimum performance when used in stabilization applications. Produced from the first quality raw materials, they provide the perfect balance of strength and separation in styles capable of functioning exceptionally well in a wide range of performance requirements. They resist ultraviolet, biological degradation, and rotting, and are chemically inert to any natural bases or acids.

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)
Grab Tensile	ASTM D 4632	lbs (N)	350 x 200 (1,557 x 890)
Grab Elongation	ASTM D 4632	%	15 x 15
CBR Puncture Resistance	ASTM D 6241	lbs (N)	800 (3,559)
Trapezoidal Tear	ASTM D 4533	lbs (N)	100 x 70 (445 x 312)
Permittivity*	ASTM D 4491	1/sec	0.5
Water Flow*	ASTM D 4491	gpm/ft² (lpm/m²)	60 (2,460)
Apparent Opening Size (AOS)	ASTM D 4751	US Sieve (mm)	40 (.425)
U.V. Resistance	ASTM D 4355	%/hrs	90/500
Percent Open Area (POA)	COE-02215	%	6
TYPICAL ROLL DIMENSIONS			
Roll Dimensions		ft (m)	6 x 300 (1.83 x 91.5) 12 x 300 (3.65 x 91.5)
Roll Area		Yd² (m²)	200 (167) 400 (334)
Estimated Roll Weight		lbs	260

## NOTES:

ARV. Minimum Average Roll Value.

Maximum average roll value ASTM D 4751- AOS.

 $\hbox{Mullen Burst ASTM D 3768 has been removed. It is not recognized by ASTM D 35 on Geosynthetics.}\\$ 

 $Puncture ASTM \ D\ 4833\ has\ been\ removed.\ It\ is\ not\ recognized\ by\ AASHTO\ M288\ and\ has\ been\ replaced\ with\ CBR\ Puncture\ ASTM\ D\ 6241.$ 

This data is provided for informational purposes only. Titan Environmental Containment Ltd. makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Titan Environmental Containment Ltd. for current updates.

## **Titan Environmental Containment**

 $<sup>^*</sup>$ At time of manufacturing. Handling, storage, and shipping may change these properties.