

# TE-PVC 50

## 50mil POLYVINYL CHLORIDE LINER



TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)
Thickness	ASTM D 5199	mil (mm)	50 ± 2.5 (1.27 ± 0.06)
Tensile Properties: Strength at Break Elongation Modulus @ 100%	ASTM D 882 Min	lbs/in (kN/m) % lbs/in (kN/m)	116 (20.3) 430 50 (8.8)
Tear Strength	ASTM D 1004 min	lbs (N)	13 (58)
Dimensional Stability	ASTM D 1204 Max Chg	%	3
Low Temperature Impact	ASTM D 1790 Pass	°F (°C)	-20 (-29)
<b>INDEX PROPERTIES</b>			
Specific Gravity	ASTM D 792 Typical	g/cc	1.2
Water Extraction % loss (max)	ASTM D 1239 Max Loss	%	0.20
Average Plasticizer Molecular Weight	ASTM D 2124		400
Volatility Loss	ASTM D 1203 Max loss	%	0.5
Soil Burial: Break Strength Elongation Modulus @ 100%	G 160 max chg	% % %	5 20 20
Hydrostatic Resistance	ASTM D 751 min	psi (kPa)	150 (1030)
<b>SEAM STRENGTHS</b>			
Shear Strength	ASTM D 882 min	lbs/in (kN/m)	96 (17)
Peel Strength	ASTM D 882 min	lbs/in (kN/m)	15 (2.6)

This data is provided for informational purposes only. Titan makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with us for current updates.

### TITAN ENVIRONMENTAL CONTAINMENT

Toll Free: 1-866-327-1957 | Email: [info@titanenviro.com](mailto:info@titanenviro.com) | Web: [www.titanenviro.com](http://www.titanenviro.com)

(Rev. April, 2018)

TRUST. QUALITY. VALUE