

TE-W315

Turbidity Curtain



TESTED PROPERTY	TEST METHOD	UNIT	VALUE
FLOAT			
Material	-	-	Expanded Polypropylene
Size	-	-	100 mm x 100 mm
Buoyancy	ASTM D 3575	kg/m	9
Float Cover	Reinforced Polyethylene	-	
Float Cover Thickness	-	mm	0.3048
Cover's Color	-	-	Yellow
U.V. Resistance (2000 hrs)	ASTM G-53	%	80
BODY FABRIC			
Material	-	-	Woven Geotextile W315
Grab Tensile Strength	ASTM D 4632	N	1400
Water Flow Rate	ASTM D 4491	l/min/m ²	163
Apparent Opening Size	ASTM D 4751	Mm	0.425
REINFORCEMENTS			
Material	-	-	Reinforced Polyethylene
Thickness	-	mm	0.4064
U.V. Resistance (2000 hrs)	ASTM D-53	%	80
GROMMETS, PINS & SEAMS			
Grommets	-	-	#3 plated brass or oxide
Seam	-	-	Double Lock Stitch
Thread	-	-	Nylon BST-207
Pins	-	-	12 mm self-blocking steel
Top load line	-	-	12 mm polypropylene rope

This data is provided for informational purposes only. Titan Environmental Containment Ltd. makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Titan Environmental Containment Ltd. for current updates.

TITAN ENVIRONMENTAL CONTAINMENT

Toll free: 1-866-327-1957 / Email: info@titanenviro.ca / Web: www.titanenviro.ca

TRUST.QUALITY.VALUE