

TE-3.1

3.1oz CIVIL NONWOVEN GEOTEXTILE



Titan has provided the containment and erosion control industries with the highest quality geotextiles available. Our nonwoven needle punched geotextiles are manufactured using polypropylene fibers, which are formed into a dimensionally stable network which allows the fibers to maintain their relative position. These products resist ultraviolet deterioration, rotting, biological degradation, and are inert to commonly encountered soil chemicals.

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)
Tensile Strength (Grab)	ASTM D 4632	lbs (N)	80 (355)
Elongation	ASTM D 4632	%	50
CBR Puncture	ASTM D 6241	lbs (N)	210 (934)
Trapezoid Tear	ASTM D 4533	lbs (N)	30 (134)
U.V. Resistance	ASTM D 4355	%/hrs	70/500
Apparent Opening Size (AOS)*	ASTM D 4751	U.S. Sieve (mm)	50 (0.30)
Permittivity	ASTM D 4491	sec 1	2.2
Water Flow	ASTM D 4491	gpm/ft ² (l/min/m ²)	150 (6112)
TYPICAL ROLL DIMENSIONS			
Roll Dimensions		ft	12.5 x 360 15 x 300
Roll Area		yd ²	500/600
Estimated Roll Weight		lbs	125/145

NOTES:

MARV. Minimum Average Roll Value.

Maximum average roll value ASTM D 4751- AOS.

Mullen Burst ASTM D 3768 has been removed. It is not recognized by ASTM D 35 on Geosynthetics.

Puncture ASTM D 4833 has been removed. It is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D 6241.

This data is provided for informational purposes only. Titan makes no warranties as to the suitability or the fitness for a specific use or 3.1 merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with us for current updates.

TITAN ENVIRONMENTAL CONTAINMENT

Toll Free: 1-866-327-1957 | Email: info@titanenviro.com | Web: www.titanenviro.com

(Rev.2021)

TRUST. QUALITY. VALUE