

TE-M60

MONOFILAMENT GEOTEXTILE



Titan's Monofilament Geotextiles are manufactured using high tenacity monofilament polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. These fabrics offer optimum performance when used in stabilization applications. Produced from the first quality raw materials, they provide the perfect balance of strength and separation in styles capable of functioning exceptionally well in a wide range of performance requirements. They resist ultraviolet and biological degradation, and rotting, and are chemically inert to any natural bases or acids.

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)
Grab Tensile	ASTM D 4632	lbs (N)	350 x 200 (1,557 x 890)
Grab Elongation	ASTM D 4632	%	15 x 15
Trapezoidal Tear	ASTM D 4533	lbs (N)	100 x 70 (445 x 312)
CBR Puncture Resistance	ASTM D 6241	lbs (N)	800 (3,559)
Permittivity*	ASTM D 4491	sec ⁻¹	0.5
Water Flow*	ASTM D 4491	gpm/ft ² (lpm/m ²)	60 (2,460)
Apparent Opening Size (AOS)	ASTM D 4751	U.S. Sieve (mm)	40 (.425)
Percent Open Area (POA)	COE-02215	%	6
U.V. Resistance	ASTM D 4355	%/hrs	90/500
TYPICAL ROLL			
Roll Width		ft (m)	6 x 300 (1.83 x 91.5) 12 x 300 (3.65 x 1.5)
Roll Area		yd ² (m ²)	200 (167) 400 (334)
Estimated Roll Weight		lbs	260

NOTES:

MARV. Minimum Average Roll Value.

Maximum average roll value ASTM D 4751- AOS.

Mullen Burst ASTM D 3768 has been removed. It is not recognized by ASTM D 35 on Geosynthetics.

Puncture ASTM D 4833 has been removed. It is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D 6241.

*At time of manufacturing. Handling, storage, and shipping may change these properties.

This data is provided for informational purposes only. Titan makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with us for current updates.

TITAN ENVIRONMENTAL CONTAINMENT

Toll Free: 1-866-327-1957 | Email: info@titanenviro.com | Web: www.titanenviro.com

(Rev. May 2022)

TRUST. QUALITY. VALUE