



## Multi-Flow Technical Properties

### Drainage Core

Property	Test Method	Value
Thickness, inches.....	ASTM D-1777.....	1.0
Flow Rate, gpm/ft *.....	ASTM D-4716.....	29
Compressive Strength, psf.....	ASTM D-1621 (sand method).....	6000
Perforations / sq. ft.....		>300

### Geo-Textile Filter

Property	Test Method	Value
Weight (oz/sq2).....	ASTM D-3776.....	4
Tensile Strength, lb. ....	ASTM D-4632.....	100
Elongation, %.....	ASTM D-4632.....	50
Puncture, lb.....	ASTM D-4833.....	50
Mullen Burst, psi.....	ASTM D-3786.....	200
Trapezoidal Tear, lb.....	ASTM D-4533.....	42
Coefficient of Perm, cm/sec.....	ASTM D-4491.....	0.1
Flow Rate, gpm/ft2.....	ASTM D-4491.....	100
Permittivity, 1/sec.....	ASTM D-4491.....	1.8
A.O.S. Max US Std Sieve.....	ASTM D-4751.....	70
UV Stability, 500 hrs., %.....	ASTM D-4355.....	70
Seam Strength, lb./ft.....	ASTM D-4595.....	100
Fungus.....	ASTM G-21.....	No Growth

All values given represent minimum average roll values

\* Horizontal Installation, gradient = 0.1, pressure = 10 psi for 100 hours



Multi-Flow products are manufactured exclusively by Varicore Technologies, Inc.

All Rights Reserved. 2016

