

# SPARTAN ROAD GRID™ 10C

FIBERGLASS GEOGRID COMPOSITE SYSTEM



Spartan Road Grid™ 10C composite system is a bi-axial geogrid bonded to a needle-punched non-woven geotextile. It is specifically designed for asphalt reinforcement with an additional moisture-proofing benefit. Its composite characteristic provides a continuous non-deforming water-resistant barrier. Spartan Road Grid™ 10C is polymer coated which ensures proper adhesion to the asphalt layers over the tack coat surface, and further optimizes the chemical compatibility between the fiberglass reinforcement and the pavement overlay to create a solid bond of the asphalt layers over the tack coat surface. This bond ensures that the reinforcing grid can effectively accept and distribute tensile stresses.

This system offers excellent heat resistance, minimal shrinkage at high temperatures, high chemical, physical and biological durability along with optimal elastic modulus and aperture size. It is biologically unaffected by soil micro-organisms, inert to all chemicals normally found in the soil, and formulated to resist ultraviolet degradation.

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)	
			MD	XD
Ultimate Tensile Strength <sup>(1)</sup>	ASTM D 6637	lbs/ft (kN/m)	571 (100.0)	571 (100.0)
Tensile Strength at 2% Strain <sup>(1)</sup>	ASTM D 6637	lbs/ft (kN/m)	456 (80.0)	456 (80.0)
Secant Stiffness EA at 2% Strain	ASTM D 6637	lbs/ft (kN/m)	22,847 (4,000)	22,847 (4,000)
Coating			Polymeric	
Elongation at Break <sup>(2)</sup>	ASTM D 6637	%	< 3	
Optimum Elasticity Modulus <sup>(2)</sup>		psi (MPa)	10.6 x 10 <sup>6</sup> (73,000)	
Melting Point Coating	ASTM D 276	°F (°C)	> 752 (> 400)	
Melting Point Glass	ASTM D 338	°F (°C)	> 1,508 (> 820)	
Asphalt Retention	ASTM D 6140	gal/yd <sup>2</sup> (l/m <sup>2</sup> )	0.3 (1.35)	
Aperture Size	Nominal	inch (mm)	0.5 (12.7)	0.5 (12.7)
Mass/Unit Area <sup>(2)</sup>	ASTM D 5261	oz/yd <sup>2</sup> (g/m <sup>2</sup> )	16.9 (570)	
TYPICAL ROLL DIMENSIONS				
Roll Width		ft (m)	12.95 (3.95)	
Roll Length		ft (m)	164.04 (50.0)	

Notes:

1. MARV – Minimum Average Roll Values

2. Mean

3. Minimum

4. Typical. Standard roll dimensions are shown. The products can be fabricated to custom lengths and widths to meet customer needs

This data is provided for informational purposes only. Titan Environmental Containment Ltd. makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Titan Environmental Containment Ltd. for current updates.

## Titan Environmental Containment

Toll free: 1-866-327-1957 | info@titanenviro.com | [TitanEnviro.com](http://TitanEnviro.com)