## TE-3x3HF HIGH STRENGTH WOVEN GEOTEXTILE



Titan 3x3HF is manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. Titan 3x3HF resists ultraviolet deterioration, rotting and biological degradation and is inert to commonly encountered soil chemicals.

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)
Grab Tensile	ASTM D 4632	lbs (N)	450 x 350 (2003 x 1558)
Grab Elongation	ASTM D 4632	%	15 x 6
CBR Puncture Resistance	ASTM D 6241	lbs (N)	1600 (7120)
Wide Width Tensile	ASTM D 4595	lbs/ft (kN/m)	3600 x 3600 (52.5 x 52.5)
Wide Width Elongation	ASTM D 4595	%	15 x 10
Wide Width Tensile (5% strain)	ASTM D 4595	lbs/ft (kN/m)	1392 x 1740 (20.3 x 25.4)
Trapezoidal Tear	ASTM D 4533	lbs (N)	180 x 140 (801 x 623)
Permittivity*	ASTM D 4491	1/sec	0.52
Water Flow*	ASTM D 4491	gpm/ft <sup>(2)</sup> (lpm/m <sup>(2)</sup> )	40 (1630)
Apparent Opening Size (AOS)	ASTM D 4751	US Sieve (mm)	30 (0.60)
UV Resistance	ASTM D4355	%/hrs	80/500
TYPICAL ROLL DIMENSIONS			
Roll Width		ft (m)	15 (4.57)
Roll Length		ft (m)	300 (91.5)

## NOTES:

ARV. Minimum Average Roll Value.

Maximum average roll value ASTM D 4751- AOS.

Mullen Burst ASTM D 3768 has been removed. It is not recognized by ASTM D 35 on Geosynthetics.

Puncture ASTM D 4833 has been removed. It is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D 6241.

This data is provided for informational purposes only. Titan Environmental Containment Ltd. makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Titan Environmental Containment Ltd. for current updates.

## **Titan Environmental Containment**