

TE-W250

WOVEN GEOTEXTILE



TE-W250 is manufactured using high-tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. TE-W250 resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

| TESTED PROPERTY | TEST METHOD | UNIT ENGLISH (METRIC) | VALUE ENGLISH (METRIC) |
|-----------------------------|-------------|---|-------------------------------------|
| Grab Tensile | ASTM D 4632 | lbs (N) | 250 (1113) |
| Grab Elongation | ASTM D 4632 | % | 12 |
| Trapezoidal Tear | ASTM D 4533 | lbs (N) | 90 (400) |
| CBR Puncture Resistance | ASTM D 6241 | lbs (N) | 750 (3338) |
| Permittivity* | ASTM D 4491 | 1/sec | 0.05 |
| Water Flow* | ASTM D 4491 | gpm/ft ⁽²⁾ (l/min/m ⁽²⁾) | 4 (163) |
| Apparent Opening Size (AOS) | ASTM D 4751 | US Sieve (mm) | 40 (.425) |
| UV Resistance | ASTM D 4355 | %/hrs | 70/500 |
| TYPICAL ROLL DIMENSIONS | | | |
| Roll Dimensions | | ft | 12.5 x 360 15 x 300 175 x 258 |
| Roll Area | | yd ⁽²⁾ | 500 |
| Estimated Roll Weight | | lbs | 310 |

NOTES:

ARV. Minimum Average Roll Value.

Maximum average roll value ASTM D 4751- AOS.

Mullen Burst ASTM D 3768 has been removed. It is not recognized by ASTM D 35 on Geosynthetics.

Puncture ASTM D 4833 has been removed. It is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D 6241.

This data is provided for informational purposes only. Titan Environmental Containment Ltd. makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Titan Environmental Containment Ltd. for current updates.

Titan Environmental Containment

Toll free: 1-866-327-1957 | info@titanenviro.com | TitanEnviro.com