

# TITAN 40-100 MIL LLDPE

Smooth Geomembrane



Our smooth linear low-density polyethylene (LLDPE) geomembrane is manufactured with the highest quality resin specifically formulated for flexible geomembranes. This product is used in applications that require increased flexibility and elongation properties where differential or localized subgrade settlements may occur such as landfill closure applications.

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)			
			40 mil	60 mil	80 mil	100 mil
Thickness Lowest individual reading	ASTM D 5199	mil	40 36	60 54	80 72	100 90
Density (max.)	ASTM D 1505	g/cm <sup>3</sup>	0.939	0.939	0.939	0.939
Tensile Properties (both directions) Strength at Break Elongation at Break	ASTM D 6693 Type IV Dumbbell, 2 ipm G.L.2.0 in	lb/in-width %	152 800	228 800	304 800	380 800
Tear Resistance	ASTM D 1004	lbs (N)	22	33	44	55
Puncture Resistance	ASTM D 4833	lbs (N)	56	84	112	140
Carbon Black Content	ASTM D 1603*/421 8	% (range)	2.0-3.0	2.0-3.0	2.0-3.0	2.0-3.0
Carbon Black Dispersion (Category)	ASTM D 5596	%/hrs	Note <sup>1</sup>	Note <sup>1</sup>	Note <sup>1</sup>	Note <sup>1</sup>
Oxidative Induction Time	ASTM D 3895, 200°C; O <sub>2</sub> , 1 atm	minutes	>100	>100	>100	>100
<b>TYPICAL ROLL DIMENSIONS</b>						
Roll Length <sup>2</sup>		ft (m)	870	560	430	340
Roll Width <sup>2</sup>		ft (m)	22.5	22.5	22.5	22.5
Roll Area		ft <sup>2</sup>	19,575	12,600	9,675	7,650

**NOTE:**

- (1) Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.
- (2) Roll lengths and widths have a tolerance of ±1%.
- GSE UltraFlex is available in rolls weighing approximately 3,900 lb.
- All GSE geomembranes have dimensional stability of ±2% when tested according to ASTM D 1204 and LTB of <-77°C when tested according to ASTM D 746.
- \*Modified.

This data is provided for informational purposes only. Titan Environmental Containment Ltd. makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Titan Environmental Containment Ltd. for current updates.

## Titan Environmental Containment

Toll free: 1-866-327-1957 | info@titanenviro.com | [TitanEnviro.com](http://TitanEnviro.com)