

Titan's 60HD SST/DST is manufactured with the highest quality resin specifically formulated for flexible geomembranes. This product is used in applications that require increased frictional resistance, excellent chemical resistance and endurance properties. This product specification meets GRI-GM13. Single Sided (SST) and Double Sided (DST).

TESTED PROPERTY	TEST METHOD	FREQUENCY	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)
	-			
Thickness (nominal) Thickness (min avg) Thickness (min 8 of 10) Thickness (lowest individual)	ASTM D 5994	every roll	mil (mm)	60 (1.5) 57 (1.43) 54 (1.35) 51 (1.28)
Density	ASTM D 1505	200,000 lb (90,000 kg)	g/cc, min	0.94
Tensile Properties (Each Direction) Strength at Break Strength at Yield Elongation at Break Elongation at Yield	ASTM D 6693, Type IV Dumbbell, 2 ipm G.L. 2.0in (50mm) G.L. 1.3in (33mm)	20,000 lb (9,000 kg)	lb/in-width (N/mm) lb/in-width (N/mm) % %	132 (23.1) 132 (23.1) 150 13
Tear Resistance	ASTM D 1004	45,000 lb (20,000 kg)	lbs (N)	45 (200)
Puncture Resistance	ASTM D 4833	45,000 lb (20,000 kg)	lbs (N)	120 (534)
Carbon Black Content	ASTM D 4218	20,000 lb (9,000 kg)	% (range)	2-3
Carbon Black Dispersion	ASTM D 5596	45,000 lb (20,000 kg)		Note ¹
Asperity Height	ASTM D 7466	second roll	mil (mm)	20 (0.51)
Stress Crack Resistance (SP-NTCL)	ASTM D 5397, Appendix	200,000 lb (90,000 kg)	hr	500
Oxidative Induction Time	ASTM D 3895, 200°C; O ₂ , 1 atm	200,000 lb (90,000 kg)	mins	≥140
TYPICAL ROLL DIMENSIONS				
Roll Length ²		Double-Sided Textured	ft (m)	505 (154
		Single-Sided Textured	ft (m)	530 (161)
Roll Width ²			ft (m)	23 (7)
Roll Area		Double-Sided Textured	ft ² (m ²)	11,615 (1,079)
		Single-Sided Textured	ft ² (m ²)	12,190 (1,132)

NOTES:

((1) Dispersion only applies to near-spherical agglomerates. 10 views shall be category 1 or 2.

(2) Roll Lengths and widths have a tolerance of $\pm 1\%$.

o HDPE SST/DST is available in rolls weighing approximately 4,000 lb (1,800 kg).

This data is provided for informational purposes only. Titan Environmental Containment Ltd. makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Titan Environmental Containment Ltd. for current updates.

Titan Environmental Containment