

# TE-W270

WOVEN GEOTEXTILE



TE-W270 is manufactured using high-tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. TE-W270 resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)
Grab Tensile	ASTM D 4632	lbs (N)	270 (1201)
Grab Elongation	ASTM D 4632	%	15
Trapezoidal Tear	ASTM D 4533	lbs (N)	100 (440)
CBR Puncture Resistance	ASTM D 6241	lbs (N)	850 (3783)
Permittivity*	ASTM D 4491	1/sec	0.05
Water Flow*	ASTM D 4491	gpm/ft <sup>(2)</sup> (l/min/m <sup>(2)</sup> )	4 (163)
Apparent Opening Size (AOS)	ASTM D 4751	US Sieve (mm)	40 (.425)
UV Resistance	ASTM D 4355	%/hrs	70/500
<b>TYPICAL ROLL DIMENSIONS</b>			
Roll Dimensions		ft	12.5 x 360 15 x 300 17.5 x 258
Roll Area		yd <sup>(2)</sup>	500
Estimated Roll Weight		lbs	310

**NOTES:**

ARV. Minimum Average Roll Value.

Maximum average roll value ASTM D 4751- AOS.

Mullen Burst ASTM D 3768 has been removed. It is not recognized by ASTM D 35 on Geosynthetics.

Puncture ASTM D 4833 has been removed. It is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D 6241.

This data is provided for informational purposes only. Titan Environmental Containment Ltd. makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Titan Environmental Containment Ltd. for current updates.

## Titan Environmental Containment

Toll free: 1-866-327-1957 | info@titanenviro.com | [TitanEnviro.com](http://TitanEnviro.com)