

TITAN 80HDL SST/DST

80mil HDPE LEAK LOCATION GEOMEMBRANE



Titan HDL Leak Location Textured is a co-extruded single-sided or double-sided textured, spark-testable high-density polyethylene (HDPE) geomembrane that contains an integrated, specially formulated conductive layer on the bottom surface of the geomembrane. This liner can easily be tested for post-installation damage using equipment capable of performing spark testing in the field per ASTM D 7240. This product is used in applications that require post-installation testing on the liner system to increase the quality of the project. This product specification meets GRI-GM13.

TESTED PROPERTY	TEST METHOD	FREQUENCY	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)
Thickness	ASTM D 5119	every roll	mil (mm)	80 (2.00)
Density	ASTM D 1508	200,000 lb (90,000 kg)	g/cm ³ (min)	0.940
Tensile Properties (Each Direction) Strength at Break Strength at Yield Elongation at Break Elongation at Yield	ASTM D 6693	20,000 lb (9,000 kg)	lb/in (kN/m) lb/in (kN/m) % (min) % (min)	120 (21) 168 (29) 100 12
Tear Resistance	ASTM D 1004	45,000 lb (20,000 kg)	lbs (N) (min)	56 (249)
Puncture Resistance	ASTM D 4833	45,000 lb (20,000 kg)	lbs (N) (min)	120 (534)
Carbon Black Content ¹	ASTM D 1603*/4218	20,000 lb (9,000 kg)	%	2.0 – 3.0
Carbon Black Dispersion	ASTM D 5596	45,000 lb (20,000 kg)		Note ²
Asperity Height	ASTM D 7466	second roll	mil (mm)	16 (0.41)
Notched Constant Tensile Load ³	ASTM D 5397, Appendix	200,000 lb (90,000 kg)	hr	500
Oxidative Induction Time	ASTM D 3895, 200 °C; O ₂ , 1 atm	200,000 lb (90,000 kg)	mins	>100

Notes:

(1) Leak Location may have an overall ash content greater than 3.0% due to the conductive layer. These values apply to the nonconductive layer only.

(2) Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.

(3) NCTL for Leak Location Textured is conducted on representative textured geomembrane samples.

(4) Roll lengths and widths have a tolerance of ±1%. HDPE Leak Location Textured is available in rolls weighing approximately 4,000 lb. All geomembranes have dimensional stability of ±2% when tested according to ASTM D 1204 and LT B of <-77° C when tested according to ASTM D746.

• *Modified.

This data is provided for informational purposes only. Titan Environmental Containment Ltd. makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Titan Environmental Containment Ltd. for current updates.

Titan Environmental Containment | Titan Environmental USA

Toll free: 1-866-327-1957 | info@titanenviro.com | TitanEnviro.com

Rev. March 2025